

29 – 80 RED OXIDE INHIBITIVE UNIVERSAL/TIE COAT PRIMER

DESCRIPTION: PICCO 29 – 80 Red Oxide Inhibitive Universal/Tie Coat provides excellent corrosion protection of steel surfaces and can be top coated with alkyds, epoxies, or polyurethanes. PICCO 29 – 80 Red Oxide Inhibitive Universal/Tie Coat Primer is formulated with a corrosion inhibiting pigment that helps protect steel surfaces even in harsh marine environments. It provides excellent corrosion protection in mild chemical environments and is therefore widely recommended for all types of industrial applications. This product meets the requirements of Federal Specification #TT-P-664.

TYPICAL USES INCLUDE

Storage Tanks and Piping
Machinery and Equipment

Structural Steel and Bridges
Marine Vessels

Industrial Equipment
General Purpose Shop Primer

TYPICAL PHYSICAL PROPERTIES:

COLOR:	Reddish-Brown
COMPONENTS:	One
GLOSS:	Flat
MIXING RATIO (BY VOL.):	N/A
WT./GALLON:	10.7 lbs
POT LIFE:	N/A
VISCOSITY AT 77° F:	68 KU
SHELF LIFE:	2 Years
SOLIDS BY WEIGHT:	60%
TEMP. RESISTANCE:	225° F
SOLIDS BY VOLUME:	36%
CHEM. RESISTANCE:	Moderate
THEORETICAL COVERAGE:	690 ft ² /gal @ 1 mil dft
FLASH POINT:	85° F, TCC
V.O.C.:	4.6 lbs/gal

RECOMMENDED D.F.T.: 1.5 – 2 mils
DRY TIME: @ 77° F, 55% R.H.

To Touch: 5 - 15 Minutes
To Handle: 1 - 2 Hours
To Recoat: Acrylic and Alkyds: 1 – 2 Hours
Epoxies and Polyurethanes: Overnight

THINNING: Brush: T-43 (not recommended)
Spray: T-42

APPLICATION METHODS:
Spray, Dip, Electrostatic Spray

FILM THICKNESS:

Wet: 4.0 – 5.5 mils
Dry: 1.5 – 2.0 mils

APPLICATION EQUIPMENT:

CONVENTIONAL: DeVilbiss 510 Gun
E Tip + Needle, 704 Air Gap

AIRLESS: Graco 30:1 Pump, 613 Tip
or equivalent

CLEANING OF EQUIPMENT:

T-42 or T-73

PACKAGING:

1 Gallon Cans

5 Gallon Pails

55 Gallon Drums

APPLICATION CONDITIONS:

Surface should be dry, above 40° F and at least 5° F above the dew point.

SURFACE PREPARATION:

Remove all grease, oil, dirt, dust or other contaminants.

PREFERRED: SSPC-SP6 Commercial Blast Cleaning

MINIMUM: SSPC-SP2 and 3 Hand and Power Tool Cleaning

PREVIOUSLY PAINTED SURFACES:

Remove all grease, oil, dirt, dust or other contaminants by Hand or Power Tool Cleaning.

Surface must be clean and dry, SSPC-SP2 or 3 or Brush-Off Blast Cleaning SSPC-SP7.

Spot prime all bare areas.

RECOMMENDED TOP COAT:

PICCO – 13, 14 or 50 – Series Enamel Topcoats

PICCO – 60 or 63 – Series Epoxy Topcoats

PICCO – 70 or 72 – Series Urethane Topcoats

SAFETY INFORMATION**DOT CLASSIFICATION: PAINT UN 1263**

DANGER: Causes eye burns and skin irritation. Vapor harmful. Dried film of this paint may be harmful if eaten or chewed. Contains organic solvent. Do not get in eyes, on skin or on clothing. Wear eye protective equipment when handling. Keep away from heat, sparks, and flame. Avoid breathing vapor or mist. Wash thoroughly after handling. Wear appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application unless air monitoring demonstrates vapor/mist levels are below applicable level. Follow respirator manufacturer's directions for use. Keep container closed. Keep out of reach of children.

FIRST AID: IN CASE OF EYE CONTACT, IMMEDIATELY FLUSH EYES WITH PLENTY OF WATER FOR AT LEAST 15 MINUTES. CALL A PHYSICIAN. FOR SKIN CONTACT, FLUSH WITH WATER AND WASH WITH SOAP AND WATER. REMOVE CONTAMINATED CLOTHING AND LAUNDER BEFORE REUSE. IF INHALED, REMOVE TO FRESH AIR. IF NOT BREATHING GIVE ARTIFICIAL RESPIRATION, PREFERABLY MOUTH-TO-MOUTH, AND CALL A PHYSICIAN.

NOTICE: Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or **fatal**.

FOR INDUSTRIAL USE ONLY