

55 – 01.BF WHITE ACRYLIC WATERBORNE BLOCK FILLER

DESCRIPTION: PICCO 55 – 01.BF is a fast drying waterborne block filler for concrete, cinder block, and other masonry surfaces. This product can be used on interior or exterior masonry surfaces and may be top coated with PICCO 55 – Series top coats or other waterborne coatings.

TYPICAL USES INCLUDE

Cinder Block Walls
Convenience Stores

Hospitals/Schools
Food Processing Plants

Warehouses
Water Treatment Plants

TYPICAL PHYSICAL PROPERTIES:

COLOR:	White
COMPONENTS:	One
GLOSS:	Flat
MIXING RATIO (BY VOL.):	N/A
WT./GALLON:	13.0 lbs
POT LIFE:	N/A
VISCOSITY AT 77° F:	110 KU
SHELF LIFE:	1 Year
SOLIDS BY WEIGHT:	68%
SOLIDS BY VOLUME:	51%
CHEM. RESISTANCE:	Moderate
THEORETICAL COVERAGE:	820 ft ² /gal @ 1 mil dft
FLASH POINT:	>200° F, TCC
V.O.C.:	1.28 lbs/gal

RECOMMENDED D.F.T.: 10 mils/coat

DRY TIME: @ 77° F, 55% R.H.

To Touch: 30 Minutes
To Handle: 2 Hours
To Recoat: 2 Hours

THINNING: Brush: T-502 or water
Spray: T-502 or water

APPLICATION METHODS:

Brush, Spray, or Dip

FILM THICKNESS:

Wet: 18 - 20 mils per coat
Dry: 9 - 10 mils per coat

APPLICATION EQUIPMENT:

CONVENTIONAL: DeVilbiss 510 Gun
E Tip + Needle, 704 Air Cap

AIRLESS: Graco 30:1 Pump, 615 Tip
or equivalent

CLEANING OF EQUIPMENT:

T-502 or water

PACKAGING:

1 Gallon Cans

5 Gallon Pails

55 Gallon Drums

APPLICATION CONDITIONS:

Surface should be dry, above 40° F and at least 5° F above the dew point.

Protect From Freezing.

SURFACE PREPARATION:

Remove all grease, oil, dirt, dust or other contaminants.

NORMAL SERVICE: For highly porous surfaces, clean with detergent wash followed by water blast, steam, or high pressure, oil-free air. If any grease or oils are present, use an industrial degreaser to remove them.

PREVIOUSLY PAINTED SURFACES:

Remove all grease, oil, dirt, dust or other contaminants. Surface must be clean and dry. Remove all rust, rust scale, chalk, and loose peeling paint by SSPC-SP2 and 3 Hand and Power Tool Cleaning, or SSPC-SP7 Brush-Off Blast Cleaning.

RECOMMENDED PRIMER / TOP COAT:

Topcoat with PICCO 55-Series Waterborne Coatings or Waterborne Epoxy Enamels.

SAFETY INFORMATION**DOT CLASSIFICATION: PAINT UN 1263**

DANGER: Causes eye burns and skin irritation. Vapor harmful. Dried film of this paint may be harmful if eaten or chewed. May contain organic solvent. Some products contain lead depending upon color. Do not get in eyes, on skin or on clothing. Wear eye protective equipment when handling. Keep away from heat, sparks, and flame. Avoid breathing vapor or mist. Wash thoroughly after handling. Wear appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application unless air monitoring demonstrates vapor/mist levels are below applicable level. Follow respirator manufacturer's directions for use. Keep container closed. Where products contain lead, do not use in dwellings or on surfaces accessible to children. Keep out of reach of children.

FIRST AID: IN CASE OF EYE CONTACT, IMMEDIATELY FLUSH EYES WITH PLENTY OF WATER FOR AT LEAST 15 MINUTES. CALL A PHYSICIAN. FOR SKIN CONTACT, FLUSH WITH WATER AND WASH WITH SOAP AND WATER. REMOVE CONTAMINATED CLOTHING AND LAUNDER BEFORE REUSE. IF INHALED, REMOVE TO FRESH AIR. IF NOT BREATHING GIVE ARTIFICIAL RESPIRATION, PREFERABLY MOUTH-TO-MOUTH, AND CALL A PHYSICIAN.

NOTICE: Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or **fatal**.

FOR INDUSTRIAL USE ONLY