

70 – SERIES ALIPHATIC POLYURETHANE

DESCRIPTION: PICCO 70 – Series Aliphatic Polyurethane finish coats are two component corrosion and chemical resistant coatings that are designed for long term protection and aesthetic enhancement of structures in industrial and marine service conditions. PICCO 70 – Series Aliphatic Polyurethane offers outstanding long term weather resistance with excellent color and gloss retention. This coating is most effective when applied over PICCO 60 – Series Epoxy-Polyamide, however, it may also be applied over other suitable primers.

TYPICAL USES INCLUDE

Offshore Equipment
Petro Chemical Industries

Marine Vessels
Power Plants

Storage Tanks and Piping
Shipbuilding

TYPICAL PHYSICAL PROPERTIES:

COLOR:	Standard Colors
COMPONENTS:	Two
GLOSS:	High Gloss
MIXING RATIO (BY VOL.):	4:1
WT./GALLON:	10.1 lbs
POT LIFE:	10 hours
VISCOSITY AT 77° F:	70 KU
SHELF LIFE:	2 Years
SOLIDS BY WEIGHT:	60%
SOLIDS BY VOLUME:	46%
TEMP. RESISTANCE:	250°F
CHEM. RESISTANCE:	Aggressive Chemical Exposure
THEORETICAL COVERAGE:	740 ft ² /gal @ 1 mil dft
FLASH POINT:	50° F, TCC
V.O.C.:	4.0 lbs/gal

RECOMMENDED D.F.T.: 1.0 – 1.5 mils/coat

DRY TIME: @ 77° F, 55% R.H.

To Touch:	20 – 30 Minutes
To Handle:	2 – 4 Hours
To Recoat:	2 – 4 Hours

THINNING: Brush: T-701 (5% - 10%)
Spray: T-701 (5% - 20%)

APPLICATION METHODS:

Brush, Roll, Spray

FILM THICKNESS:

Wet:	2.0 – 4.0 mils per coat
Dry:	1.0 – 2.0 mils per coat

APPLICATION EQUIPMENT:

CONVENTIONAL: DeVilbiss 510 Gun
E Tip + Needle, 704 Air Cap
AIRLESS: Graco 30:1 Pump,
.017 - .021 Tip or equivalent

CLEANING OF EQUIPMENT:

T-701

PACKAGING:

Base: Ones – 80% Fill (0.80 gal)
Fives – 80% Fill (4.0 gal)

Activator: Quarts – 80% Fill (0.20 gal)
Ones – 100% Fill (1.0 gal)

APPLICATION CONDITIONS:

Surface should be dry, above 50° F and at least 5° F above the dew point.

SURFACE PREPARATION:

Remove all grease, oil, dirt, dust or other contaminants.

NORMAL SERVICE: SSPC – SP6 Commercial Blast Cleaning or SSPC – SP10 Near White Metal Blast Cleaning. Prime with PICCO 68 – 80 Epoxy-Polyamide Primer.

CORROSIVE SERVICE: SSPC – SP10 Near White Metal Blast Cleaning. Prime with PICCO 68 – 80 Epoxy-Polyamide Primer.

PREVIOUSLY PAINTED SURFACES:

Remove all grease, oil, dirt, dust or other contaminants. Surface must be clean and dry. Remove all rust, rust scale, chalk, and loose peeling paint by SSPC – SP2 and SP3 Hand and Power Tool Cleaning, or SSPC – SP7 Brush-Off Blast Cleaning. Spot prime all bare areas and fully prime entire area to be painted before top coating.

RECOMMENDED PRIMER:

Use PICCO 68 – 80 Epoxy-Polyamide Primer for optimum results. May also be applied over PICCO 29 – 80 Universal Primer.

SAFETY INFORMATION**DOT CLASSIFICATION: PAINT UN 1263**

DANGER: Causes eye burns and skin irritation. Vapor harmful. Dried film of this paint may be harmful if eaten or chewed. Contains organic solvent. Do not get in eyes, on skin or on clothing. Wear eye protective equipment when handling. Keep away from heat, sparks, and flame. Avoid breathing vapor or mist. Wash thoroughly after handling. Wear appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application unless air monitoring demonstrates vapor/mist levels are below applicable level. Follow respirator manufacturer's directions for use. Keep container closed. Keep out of reach of children.

FIRST AID: IN CASE OF EYE CONTACT, IMMEDIATELY FLUSH EYES WITH PLENTY OF WATER FOR AT LEAST 15 MINUTES. CALL A PHYSICIAN. FOR SKIN CONTACT, FLUSH WITH WATER AND WASH WITH SOAP AND WATER. REMOVE CONTAMINATED CLOTHING AND LAUNDER BEFORE REUSE. IF INHALED, REMOVE TO FRESH AIR. IF NOT BREATHING GIVE ARTIFICIAL RESPIRATION, PREFERABLY MOUTH-TO-MOUTH, AND CALL A PHYSICIAN.

NOTICE: Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or **fatal**.

FOR INDUSTRIAL USE ONLY